

Phosphor Bronze C51000 Spring Hard

- Temper: S
- Density: .320 lb/in<sup>3</sup> (8.86 g/cm<sup>3</sup>)
- Yield Strength (0.2% offset): 74-88 ksi (52-56 kg/mm<sup>2</sup>)
- Ultimate Tensile Strength: 76-91 ksi (53-64 min. kg/mm<sup>2</sup>)
- Thermal Conductivity: 40 BTU/ft.hr.F (70 W/m.K)